

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES


Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Problem Image Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 864 362 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
05.11.2003 Bulletin 2003/45

(51) Int Cl.7: **B01J 31/06, B01J 37/02,
B01J 35/02**

(21) Application number: **98301695.7**

(22) Date of filing: **09.03.1998**

(54) **Process for producing a composite structure consisting of metallic nanoparticles coated with an organic polymer**

Herstellungverfahren einer Verbundstruktur bestehend aus metallischen Nanopartikeln umhüllt mit einem organischen Polymer

Procédé de préparation d'une structure composite à base de nanoparticules métalliques enrobées d'un polymère organique

(84) Designated Contracting States:
DE FR GB

(30) Priority: **10.03.1997 JP 5523497**
29.05.1997 JP 14019397
22.08.1997 JP 24187297
22.08.1997 JP 24187397

(43) Date of publication of application:
16.09.1998 Bulletin 1998/38

(73) Proprietors:
• **Japan Science and Technology Corporation**
Kawaguchi-shi, Saitama-ken 332-0012 (JP)
• **DAICEL CHEMICAL INDUSTRIES, LTD.**
Sakai-shi Osaka-fu 590 (JP)

(72) Inventors:
• **Funaki, Yoshinori**
Shinzaike 1367-5 (JP)
• **Tsutsumi, Kiyoharu, Postal Code 631-0006**
Gurandoparesu-gakuenmae D-511 (JP)
• **Hashimoto, Takeji**
Yoshida Nakaoji-cho 19 (JP)

• **Harada, Masafumi**
Horai 1-9-10 (JP)

(74) Representative: **Lawrence, John Gordon et al**
Lloyd Wise, McNeight & Lawrence
Regent House
Heaton Lane
Stockport, Cheshire SK4 1BS (GB)

(56) References cited:
US-A- 4 252 677 **US-A- 5 234 758**

• **ANTONIETTI M: "SYNTHESIS AND CHARACTERIZATION OF NOBLE METAL COLLOIDS IN BLOCK COPOLYMER MICELLES"" ADVANCED MATERIALS, vol. 7, no. 12, 1 December 1995, pages 1000-1005, XP000547224**
• **R. SAITO ET AL.: "Introduction of colloidal silver into the poly(2-vinylpyridine) microdomain of microphase-separated poly(styrene-b-2-vinylpyridine) film. One step method." POLYMER, vol. 36, no. 21, 1995, pages 4119-4124, XP002064963**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 864 362 B1

Description

BACKGROUND OF THE INVENTION

5 Field of the Invention

[0001] The present invention relates to a novel metal-organic polymer composite structure, particularly a porous metal-organic polymer composite structure, which can be utilized as functional materials such as catalysts, fixed catalysts, membrane reactors, antistatic plastics and other applications, and a method for producing the same.

10 Prior Art

[0002] Ultrafine metal particles including noble metal particles are widely used as catalysts, and it is known that the smaller the particle size is, the higher the catalyst activity per unit weight is. In this case, since an ultrafine metal particle having a particle size of nm order tends to coagulate due to bonding of metal atoms on its surface and it is difficult for the particle to exist in stable manner without any treatment, protection and stabilization using a surfactant and a polymer such as poly(N-vinyl-2-pyrrolidone), poly(2-vinylpyridine) and the like have been tried (Mathias Brust et al., J. Chem. Soc., Chem. Commun., 801, 1994; Naoki Toshima et. al., Chemistry Letters, 1245, 1985). Since ultrafine metal particles thus obtained are usually in a uniform solution, separation from a reaction product is difficult when the particles are used as a catalyst, and for industrial use, a support such as silica gel, polymer on the like is desired. Therefore, it is preferable that the support is composed of a microporous material having a large specific surface area, and consequently, inorganic materials such as silica gel, activated carbon, alumina and the like have been hitherto used. However, these inorganic materials have problems in molding properties and processing properties since they are powders themselves, and for use as a film or membrane, a support by a polymer is required.

[0003] Typical examples of methods for producing a microporous film composed of a polymer include the following.

(1) Japanese Patent Application Laid-Open (JPA) No. 1,739/1989

[0004] Described is a method for producing a porous material by microphase separation of a block copolymer composed of a styrene derivative and a conjugated diene or acrylate derivative, and by hydrolysis and treatment of the conjugated diene or acrylate derivative with plasma containing oxygen.

(2) JPA No. 279,741/1990

[0005] Described is a method in which a mixture of a first polymer having an ionic-bonding functional group on each end of the polymer and a second polymer having a functional group on each end capable of bonding to the afore-said functional group of the first polymer is subjected to a solution casting, one phase of the microphase-separated structure formed in the resulting film is treated with a base or acid to cut the bonding of the block copolymer, and the treated phase is extracted with a solvent.

(3) JPA No. 287,084/1993

[0006] Described is method for producing a porous film having a pore size of several hundreds nm which has expectantly the possibility as a carrier for a catalyst. This method is characterized in that the film has a bicontinuous structure of various microphase-separated structures to be formed by a block copolymer, one component is decomposed or eluted, and the pore size distribution is very narrow due to the bicontinuous structure.

[0007] As for fixing ultrafine metal particles on such a support, although physical adsorption on the surface of the support is most simple, the supported ultrafine metal particles tend to flow out of the system in such method.

[0008] For preventing it, ultrafine metal particles are preferably fixed on the support through some chemical bond. As a specific method for chemically fixing ultrafine metal particles, there has been reported a method in which a support obtained by modification with imino diacetate on the surface of a copolymer of styrene and divinylbenzene is used, and then palladium ions are reduced in a water/methanol mixed solution to form palladium fine particles on the support (H. Hirai, S. Komatuzaki, and N. Toshima; Bull. Chem. Soc. Jpn., 57, 488-494, 1984). While a number of methods are thus known for ultrafine metal particles supported on the surface of a polymer, from the viewpoint of stability of ultrafine metal particles on support, supported particle inside the support is more preferable than that on the support.

[0009] As methods for introducing ultrafine metal particles inside a polymer, there are known, for example, a method in which poly(2-vinylpyridine) phase of a poly(2-vinylpyridine) / polystyrene block copolymer is crosslinked with 1,4-diiodobutane, then, fine crystals of silver iodide are deposited therein, and the crystals are reduced by photoreduction

so as to form ultrafine silver particles (R. Saito, S. Okamura and K. Ishizu, Polymer, 1993, 34-6, 1189). A method is also known in which a palladium (II) acetylacetonate complex is dissolved in a methacrylic acid monomer, polymerized and solidified with benzoyl and peroxide. Then, the solidified substance is heated to form ultra fine metal particles (Y. Nakao, Kobunshi, 43, December, pp 852-855 1994). However, the former is a peculiar method utilizing the photoreduction of silver halide fine crystal, and therefore, this method can not be generally applied to a wide range of metals including noble metals such as platinum, palladium and rhodium useful as a catalyst and other applications. The latter method, based on a synthesizing and crosslinking reaction of a homopolymer, is also inappropriate because it cannot form a porous material to be used as a catalyst and other applications.

Summary of the Invention

[0010] According to a first aspect of the invention, there is provided a method for producing a porous metal-organic polymer composite structure comprising a microphase-separated structure from a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain which are incompatible with each other are bonded together at each end, wherein ultrafine metal particles are contained in the metalphilic polymer phase of said microphase-separated structure, comprising the steps of:

i) dissolving a non-water-soluble organic polymer; a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with the non-water-soluble organic polymer;

ii) producing a solution of a melt in which said metal-organic polymer complex and a matrix block copolymer compatible with the complex are randomly mixed, and forming a microphase-separated structure from said matrix block copolymer by a solvent casting or a decrease in temperature, thereby introducing the ultrafine metal particles into the metalphilic polymer phase; and

iii) removing the metalphobic polymer phase from said microphase-separated structure for pore formation by eluting or decomposing said metalphobic polymer phase.

[0011] According to a second aspect of the invention there is provided a method for producing a porous metal-organic polymer composite structure comprising a microphase-separated structure from a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain which are incompatible with each other are bonded together at each end, wherein ultrafine metal particles are contained in the metalphilic polymer phase of said microphase-separated structure comprising the steps of:

i) dissolving a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with said block copolymer, and

ii) producing a solution or a melt in which said metal-organic polymer complex is randomly mixed, and forming a microphase-separated structure from said metal-organic polymer complex by a solvent casting or a decrease in temperature, and

iii) removing the metalphobic polymer phase from said microphase-separated structure for pore formation by eluting or decomposing said metalphobic polymer phase.

[0012] The present invention solves the above-described problems in the conventional art, by providing a novel type of metal-organic polymer composite structure, particularly a porous metal-organic polymer composite structure, in which ultrafine metal particles are contained and maintained (embedded) in a block copolymer phase, not by providing a metal-organic polymer composite in which ultrafine metal particles are attached simply on the surface of a porous support (the void wall surface) as in the above-described prior art.

[0013] More specifically, according to an embodiment of the present invention, a metal-organic polymer complex is prepared beforehand in which the outer surface of an ultrafine metal particle is coated (protectively coated) with a polymer (homopolymer) which is compatible with a polymer forming a matrix. The metal-organic polymer complex is then mixed with a block copolymer containing a polymer chain which is to form the support (the matrix). The formation of a phase-separated structure (microphase-separated structure) from the block copolymer results in a metal-organic polymer composite structure in which ultrafine metal particles are contained in a phase of the microphase-separated

structure. Further, from such metal-organic polymer composite structure (particularly the one having a bicontinuous structure), a porous structure can be obtained by eluting or decomposing the phase not containing the metal.

[0014] While the present invention thus provides a novel metal-organic polymer composite structure, particularly a porous composite structure, in which ultrafine metal particles are contained in a polymer phase, it has been found by observing this structure with a microscope that the ultrafine metal particles are located deeply inside the matrix polymer forming a network. Therefore, for example, when this metal-organic polymer composite structure, particularly a porous structure, is used as a catalyst, it is required that the reactants should invade deeply inside the matrix polymer, and the catalytic activity may not be fully manifested.

[0015] This disadvantage that "the distance between the surface of the polymer skeleton and the ultrafine metal particle is long" is solved, according to a preferred embodiment of the present invention, by preparing beforehand ultrafine metal particles coated with a specific block copolymer and introducing them into a microphase-separated structure of a matrix polymer. More specifically, a metal-organic polymer complex is prepared in which an ultrafine metal particle is coated with a block copolymer (not with the homopolymer as described above) composed of a metalphilic polymer chain and a metalphobic polymer chain, and by using this complex, the ultrafine metal particles are introduced and contained in a phase of a microphase-separated structure formed from a block copolymer which has compatibility with the polymer chain (which has coated the ultrafine metal particles) and is to form a matrix (a support). Thus, according to the present invention, there is obtained a structure (particularly, a porous structure) in which ultrafine metal particles are located near the surface (boundary) of the matrix polymer skeleton.

[0016] Furthermore, in the above-described method for forming a microphase-separated structure using a metal-organic polymer complex in which an ultrafine metal particle is coated with a non-water-soluble organic polymer (which is a homopolymer), the skeleton is disturbed and a microphase separation into "a domain in which ultrafine metal particles are condensed" and "a polymer skeleton domain in which ultrafine metal particles are contained only in a slight amount" occurs when the ultrafine metal particle content is increased. It is therefore difficult to introduce the ultrafine metal particles into the polymer skeleton matrix in an amount of 1% or more by weight. Furthermore, since the ultrafine metal particles are located inside the matrix polymer skeleton, the reactants should invade deeply into the polymer skeleton, and consequently the catalytic activity decreases when the structure is made into a porous material and used as a catalyst.

[0017] Such problems that "(1) the ultrafine metal particle content is low" and "(2) the distance between the surface of the polymer skeleton and the surface of the ultrafine metal particle is long" are also solved, according to another preferred embodiment of the present invention, by using a metal-organic polymer complex in which the surface of an ultrafine metal particle is protectively coated with a block copolymer (namely, not with a homopolymer) in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end. More specifically, taking advantage of a microphase-separated structure obtained directly from such complex, it becomes possible to produce a metal-organic polymer composite structure and a porous metal-organic polymer composite structure having a remarkably high metal content.

[0018] Thus, according to the present invention, there is provided a metal-organic polymer composite structure comprising a microphase-separated structure from a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain (which are incompatible with each other) are bonded together at each end, wherein ultrafine metal particles are contained in the metalphilic polymer phase of the microphase-separated structure. In the metal-organic polymer composite structure of the present invention the metalphobic polymer phase is subjected to pore formation to form a porous structure.

[0019] In a preferred embodiment of the metal-organic polymer composite structure of the present invention, the ultrafine metal particles are located near the skeleton surface (boundary) of the metalphilic polymer phase of the microphase-separated structure.

[0020] In another preferred embodiment of the metal-organic polymer composite structure of the present invention, the ultrafine metal particles are contained in the metalphilic polymer phase in an amount of 1% or more by weight, and they can also be contained even in an amount of 10% or more by weight.

[0021] The microphase-separated structure in the structure of the present invention is preferably of a bicontinuous structure. The ultrafine metal particles contained in the structure of the present invention usually have a particle size of 10 nm or less.

[0022] In another aspect of the present invention, there is provided a method for producing the above-described metal-organic polymer composite structure comprising the steps of i) dissolving a non-water-soluble organic polymer, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the resultant solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which an ultrafine metal particle is coated with the non-water-soluble organic polymer, and ii) producing a solution or a melt in which the above-described metal-organic polymer complex and a matrix block copolymer compatible with this complex are randomly mixed (i.e. in a disordered state), and forming a microphase-separated structure from the matrix block copolymer by a solvent casting or a decrease in temperature, respectively, thereby introducing the ultrafine metal particles into the polymer phase.

[0023] The method of the present invention usually comprises, after the formation of the microphase-separated structure, the step of iii) removing the metalphobic polymer phase from the microphase-separated structure for pore formation, so as to obtain a porous metal-organic polymer composite structure. In a preferred embodiment of the present invention, there is used a block copolymer, as the non-water-soluble organic polymer, in which a metalphilic polymer chain and a metalphobic polymer chain (which are incompatible with each other) are bonded together at each end, to consequently obtain a metal-organic polymer composite structure in which metal particles are located near the skeleton surface (boundary) of the polymer phase.

[0024] The present invention also provides a method for producing the above-described metal-organic polymer composite structure, comprising the steps of i) dissolving a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the resultant solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which the surface of an ultrafine metal particle is coated with the block copolymer, and ii) producing a solution or a melt in which the above-described metal-organic polymer complex is randomly mixed (i.e. in a disordered state), and forming a microphase-separated structure from the metal-organic polymer complex by a solvent casting or a decrease in temperature, respectively.

[0025] The method of the present invention usually comprises, after the formation of the microphase-separated structure, the step of iii) removing the metalphobic polymer phase from the microphase separated structure for pore formation, so as to obtain a porous metal-organic polymer composite structure. This method of the present invention is suitable for obtaining a metal-organic polymer composite structure having a particularly high amount of ultrafine metal particles.

[0026] In further aspect of the present invention, there is provided a metal-organic polymer complex in which an ultrafine metal particle (metal cluster) is coated with a non-water-soluble organic polymer. As such metal-organic polymer complex is preferred a complex in which the non-water-soluble organic polymer is a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain (which are incompatible with each other) are bonded together at each end. Such metal-organic polymer complex is used for producing the metal-organic polymer composite structure of the present invention, and further, is useful itself in various applications.

[0027] The present invention further provides a method for producing the above-described metal-organic polymer complex, comprising the step of dissolving a non-water-soluble organic polymer, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the solution for reduction at 50 to 120°C.

BRIEF DESCRIPTION OF THE DRAWINGS

[0028] Fig. 1 is a schematic model representing the structure of an ultrafine metal particle-block copolymer complex formed in a micelle, as is conventionally known.

[0029] Fig. 2 is a schematic model representing the structure of a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with a block copolymer, according to a preferred embodiment of the present invention.

[0030] Fig. 3 shows a transmission electron microphotograph (left) and a schematic model thereof (right), both representing the structure of a metal-organic polymer composite structure obtained by using a matrix polymer and a metal-organic polymer complex in which an ultrafine metal particle is coated with a homopolymer.

[0031] Fig. 4 shows a transmission electron microphotograph (left) and a schematic model thereof (right), both representing the structure of a metal-organic polymer composite structure obtained by using a matrix polymer and a metal-organic polymer complex in which an ultrafine metal particle is coated with a block copolymer according to a preferred embodiment of the present invention.

[0032] Fig. 5 shows a scanning electron microphotograph (A) and a transmission electron microphotograph (B), representing the structure of a porous metal-organic polymer composite structure containing a high amount of metal obtained by using only a metal-organic polymer complex in which an ultrafine metal particle is coated with a block copolymer according to a preferred embodiment of the present invention.

Detailed Description of the Invention

[0033] While the present invention provides a novel metal-organic polymer composite structure, particularly a porous metal-organic polymer composite structure, by utilizing a metal-organic polymer complex (organic polymer-protected metal cluster) in which an ultrafine metal particle (metal cluster) is coated with a non-water-soluble organic polymer, such metal-organic polymer complex itself is also useful as a catalyst, a nonlinear optical material, an electroconductive plastic, an antistatic material, a plastic filler and other applications.

[0034] As described in the beginning, in order to stabilize ultrafine metal particles having a small particle size without coagulating each other for use as a catalyst and other applications, the following examples of metal clusters protected

by a polymer, as well as microphase-separated structures, have been hitherto known.

(i) Metal clusters protected with a water-soluble polymer (Naoki Toshima et. al., Z. Naturforsch, 50a, 283, 1995):

[0035] Described is a method in which a noble metal salt such as palladium chloride, hexachloroplatinic acid and the like is used together with poly(N-vinyl-2-pyrrolidone) to prepare an aqueous solution, and the solution is subjected to reduction by alcohol to form metal clusters protected with poly(N-vinyl-2-pyrrolidone). The metal clusters thus formed are water-soluble. However, most of synthetic polymers which are industrially used are non-water-soluble, such as even polymers having a relatively high polarity such as poly(methyl methacrylate), polyvinylpyrrolidone and the like, not to mention non-polar polymers such as polystyrene, polybutadiene, polyisoprene and the like. Therefore, there is a problem that uniform colloidal dispersion in these synthetic polymers can not be formed by using metal clusters protected with such water-soluble polymer.

(2) Cluster formation by reduction of a metal salt in a micellar polymer formed in an organic solvent (Markus Antonietti et al., Advanced Materials, 1000, 7, No. 12, 1995):

[0036] A micelle in which a metal salt is contained in an organic solvent is formed by vigorously mixing an aqueous solution of the metal salt such as chloroauric acid with a block copolymer composed of polystyrene and polyvinylpyridine in a toluene/tetrahydrofuran mixed solution. Reaction with a reducing agent such as NaBH_4 and N_2H_4 results in the formation of metal cluster stabilized in the micelle. However, since the cluster is formed inside the polymer micelle in this method, the size of the cluster depends on such factors as the size of the micelle and the stoichiometrical relation between the metal salt and the metal bonding sites. This method therefore suffers a drawback that the control of the cluster size is difficult.

[0037] In addition, this reference discloses neither a method for producing a porous metal-organic polymer composite structure nor a composite structure produced thereby. This reference relates to a polymer-protected metal cluster which is quite different from a metal-organic polymer complex as produced in the step i) of the claims of the present invention.

(3) Microphase-separated structure (R. Saito et. al., Polymer Vol.36, No. 21, pages 4119-4124(1995)).

[0038] This discloses a microphase separated from a block copolymer [poly (2-vinylpyridine/polystyrene) block copolymer]. However, the method disclosed is very different from the method of the present invention. In the method of this reference, a microphase separated structure containing silver nitrate is formed by casting a solution of silver nitrate/block copolymer in water/1,4-dioxane. The microphase-separated structure is then fixed by placing the cast film in contact with diiodobutane gas so as to crosslink the poly (2-vinylpyridine) (P2VP), whereupon fine crystals of silver iodide are deposited in the P2VP phase of the phase-separated structure through the reaction of the silver nitrate with iodine ions from the diiodobutane. The silver iodide crystals are thereafter reduced by photoreduction so as to form fine silver crystals.

[0039] Contrary to the method of the present invention, it is quite impossible, by the method as disclosed in this reference, to control the location of metal particles within the microphase-separated structure since such particles are formed from the silver iodide crystals randomly deposited in the P2VP phase. In addition, it is apparent to the skilled person that the method of this reference includes sophisticated steps for forming metal particles and is applicable only to silver which is susceptible to the specific photoreduction.

[0040] Thus, no conventional techniques have realised a polymer-protected metal cluster in which the metal cluster exists in a stable manner, the control of the cluster size is easy, and the dispersion for use in a wide range of polymers is also possible.

[0041] The present invention therefore provides a polymer-protected metal cluster which has a wide range of applications including easy introduction into various polymers, due to solubility in various organic solvents, as well as a method for producing such protected cluster. The present invention has solved the problems of the prior art as described above, and it becomes possible to form a protected metal cluster having a particle size of 10 nm or less where the size distribution is narrow and even the size control of the particle is easy.

[0042] For producing a metal-organic polymer composite structure (including a porous structure) according to the present invention, it is particularly preferable to use a complex in which the surface of an ultrafine metal particle is coated with a block copolymer (block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end) as the metal-organic polymer complex (organic polymer-protected metal cluster). By this way, there can be obtained a composite structure (particularly a porous composite structure) in which ultrafine metal particles are near the skeleton of a matrix polymer, and also a composite structure (particularly a porous composite structure) containing a remarkably high amount of metal. These advantages can be accounted for as follows.

[0043] As a complex in which an ultrafine metal particle is coated (protectively coated) with a polymer, there has

been hitherto known a complex in which an ultrafine metal particle is coated with a polymer for stabilization by reduction reaction in a polymer micelle. (Markus Antonietti et. al., Advanced Materials, 1000, 7, No. 12, 1995), as described above. By such method, however, the complex in which the ultrafine metal particle is coated with the polymer (even if the polymer is a block copolymer) forms a concentric multi-layer structure (see Fig. 1).

[0044] On the other hand, in the method of the present invention, it is considered as described below that an ultrafine metal particle is coated and stabilized basically by one polymer molecule since the ultrafine metal particle is formed within a space defined by the polymer molecule present in the form of solution. Therefore, when a block copolymer in which "a metalphilic polymer chain" and "a metalphobic polymer chain" are bonded together at each end is used, only "the metalphilic polymer chain" will presumably coat the ultrafine metal particle so as to form "the head of the metal-organic polymer complex", and "the metalphobic polymer chain" is bonded to this head at its end to form "the tail of the metal-organic polymer complex" (The schematic model is shown in Fig. 2) Therefore, an ultrafine metal particle coated even with a block copolymer is not suitable for the metal-organic polymer complex to be used in the present invention (if it is formed in a micelle of such block copolymer), since the outer shell of the particle is coated with the same kind of polymer (which is incompatible with metal).

[0045] The "metal-organic polymer complex" to be used in the present invention is thus expectantly constituted of "the head portion" and "the tail portion" and the respective portions will possibly tend to be introduced into the corresponding phases compatible with the respective polymers. However, since "the head portion" and "the tail portion" are chemically bonded, the complex can not be embedded deeply into the corresponding phases, and consequently there can be obtained a structure in which the metal is located near the boundary of the polymer phase skeleton of the phase-separated structure. A porous structure can be obtained by decomposing one of the polymer phases.

[0046] Such a feature of the present invention has actually been substantiated by observing the resulting metal-organic polymer composite structure or the porous metal-organic polymer with a microscope. Fig. 3 shows a transmission electron microphotograph (left) and its schematic picture representing the photograph (right) of a structure of the present invention. The structure is obtained by introducing ultrafine metal particles (ultrafine Pd particles) coated with poly(2-vinylpyridine) (P2VP) (homopolymer) into a microphase-separated structure from a block copolymer (P2VP-b-PI) composed of poly(2-vinylpyridine) (P2VP) and polyisoprene (PI). In the photograph and the figure, the black dots indicate ultrafine metal particles, and a porous structure is obtained by decomposing the blackish phase (PI phase) to be a pore (This remark applies to Fig. 4 to be described below). From the Fig.3, it is seen that the ultrafine metal particles are located deeply inside and around the center of the P2VP phase. On the other hand, Fig. 4 shows a transmission electron microphotograph (left) and its schematic picture (right), representing the structure composed of a microphase-separated structure from P2VP-b-PI into which ultrafine Pd particles coated with P2VP-b-PI (block copolymer) is introduced, according to a preferred embodiment of the present invention. It is seen that the ultrafine metal particles (Pd) are located near the skeleton boundary of the P2VP phase.

[0047] Thus, according to the present invention, there can be obtained a porous material useful, for example, as a membrane reactor and a highly active catalyst which is easily contacted with a reactant, with supporting ultrafine metal particles strongly on a support (polymer).

[0048] Further, the metal-organic polymer complex to be used in the present invention, in which an ultrafine metal particle (metal cluster) is protectively coated with a block copolymer (block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end), is itself a kind of supermolecule, and it can be considered as a huge surfactant or a block copolymer molecule within which a metal particle is contained. Therefore, the metal-organic polymer complex itself can form a microphase-separated structure, and from such microphase-separated structure a metal-organic polymer composite structure and a porous metal-organic polymer composite structure can be produced even without using a matrix polymer. Furthermore, since ultrafine metal particles are contained from the beginning, a metal-organic polymer composite structure and a porous metal-organic polymer composite structure derived from the microphase-separated structure is considered to contain a high amount of the ultrafine metal particles.

[0049] Such a feature has actually been substantiated by observing the resulting metal-organic polymer composite structure and porous metal-organic composite structure with a microphotograph. Fig. 5 shows a scanning electron microphotograph representing the surface image (A) and a transmission electron microphotograph revealing the internal image (B) of one example of the porous metal-organic polymer composite structure obtained according to the present invention. It is seen from Fig. 5 that, in the porous structure of the present invention, a continuous fine pore (the black domain in A represents a pore region formed by the removal of metalphobic polymer phase (polyisoprene phase)) is formed, and a remarkably high amount of ultrafine metal particles (ultrafine Pd particles in this case : black dots represented in B) are uniformly dispersed therein.

[0050] Thus, according to the present invention, ultrafine metal particles can be contained in an amount of 1% or more by weight which has been impossible in the conventional structures or porous materials using a metal-organic polymer complex. Furthermore, the ultrafine metal particles can be introduced even in an amount of 10% or more by weight which is effective in the case of practical use as a catalyst and other applications. Even 50 to 60% by weight

of ultrafine metal particles can be introduced if necessary.

[0051] The metal-organic polymer composite structure and porous metal-organic polymer composite structure of the present invention will be described in detail below referring to the respective constituent components and steps for the production thereof.

(1) Preparation of metal-organic polymer complex

[0052] For preparing the metal-organic polymer complex according to the present invention, a non-water-soluble organic polymer (homopolymer or block copolymer), a solvent-soluble metal compound and a reducing agent are dissolved in an organic solvent (a common excellent solvent for these components), to prepare a solution in which the respective components are dispersed in molecular level. Then, the solution is heated for reduction to prepare a metal-organic polymer complex in which the surface of the ultrafine metal particle is coated (protectively coated) with the block copolymer or the homopolymer, and the complex is purified by such means as super-centrifugal separation.

[0053] The temperature for the heating for reduction is usually in the range of from about 50 to 120°C, and the heating time is in the range of from approximately 5 to 50 hours. As an organic solvent, various compounds can be used, which may be selected for use from hydrocarbons, aromatic hydrocarbons, halogen compounds, ether compounds, amide compounds, sulfoxide compounds and so on.

(i) Block copolymer for coating metal :

[0054] For producing a metal-organic polymer composite structure (particularly a porous metal-organic polymer composite structure) in which ultrafine metal particles are located near skeleton boundary of a polymer phase or a metal-organic polymer composite structure (particularly a porous metal-organic polymer composite structure) in which a high amount of ultrafine metal particles are contained in a polymer phase according to the preferred embodiments of the present invention, a metal-organic polymer complex is used in which the surface of an ultrafine metal particle (metal cluster) is coated with a block copolymer. This block copolymer is not particularly limited, providing it is constituted of a metalphilic block chain (polymer chain) and another block chain (polymer chain) incompatible with the metalphilic polymer.

[0055] As a polymer for constituting the metalphilic block chain, there can be exemplified by a polymer composed of a monomer unit having a nitrogen atom such as poly(2-vinylpyridine), polyaminostyrene and the like; a polymer composed of a monomer unit having an oxygen atom such as poly(methyl methacrylate) and the like; a polymer composed of a monomer unit containing sulfur such as poly(propylene sulfide). Any polymer is permissible providing it has basically affinity with metals or metal ions. A block copolymer or a random copolymer, which is obtained from a metal coordinated polymer by propagating other monomer units from the end of the polymer by living polymerization and the like, can be used. The number average molecular weight (Mn) of the metalphilic polymer chain may be from 1000 to 1000000, and preferably from 5000 to 500000. It is more preferable from 10000 to 100000 in view of the easiness for synthesis of a polymer and the stability of the resultant protected cluster (metal-organic polymer complex).

[0056] The other polymer chain (polymer for constituting a phase which is to finally form a pore) of the block copolymer is not basically limited providing it is "incompatible with an ultrafine metal particle protected with a metalphilic polymer". In a case where a pore is formed in the structure, a polymer which can be decomposed is preferred as will be described below.

[0057] The number of blocks in the block copolymer is not particularly limited. When a metal-organic polymer composite structure or porous metal-organic polymer composite structure containing a high amount of ultrafine metal particles is to be produced by the direct microphase separation from the block copolymer, an A-B type diblock copolymer or an A-B-A type triblock copolymer which tends to form a bicontinuous structure as the microphase-separated structure is preferred.

(ii) Homopolymer for coating metal

[0058] While for obtaining the metal-organic polymer composite structure or porous metal-organic polymer composite structure of the present invention, the metal-organic polymer complex coated with the block copolymer as described above (i) is preferably used, a metal-organic polymer complex coated with a homopolymer can also be used. As the homopolymer, there can be used such a polymer as has been described in (i) for constituting a metalphilic block chain.

(iii) Metal for constituting the complex

[0059] As a metal for constituting the metal-organic polymer complex coated with a block copolymer (or a homopolymer) of the present invention, various metals can be applied. Examples of usable metals include transition metals,

for example, metals of the group VIII, particularly various noble metals. In preparing the complex, the metal is dissolved as a solvent-soluble metal compound (represented by a salt or a complex thereof) in an organic solvent together with a copolymer (or a homopolymer) and a reducing agent.

[0060] Thus, according to the present invention, there can be obtained a metal-organic polymer complex in which the metal particle size is extremely small, i.e. 10 nm or less (usually several nm) and the particle size is uniform. This is because a reaction system for preparing an ultrafine metal particle protectively coated with a copolymer (or a homopolymer) is a uniform organic solvent system.

(iv) Reducing agent

[0061] As the reducing agent, various compounds such as alcohols, saccharides, ascorbic acid, hydrogen gas, hydrazine, boron hydride and the like can be used.

[0062] While the ratio of a block copolymer, a soluble metal compound, a reducing agent and a solvent to be used for producing the metal-organic polymer complex coated with a block copolymer (or a homopolymer) depends on an aimed complex, the general standard thereof is as follows.

Soluble compound/monomeric unit of copolymer (or homopolymer) = 1/4 to 1/50 (molar ratio)

Reducing agent/soluble compound = 1/10 to 1/10000 (large excess)(molar ratio)

Copolymer (or homopolymer)/solvent = 1/1000 to 1/10 (volume ratio)

(2) Matrix polymer

[0063] In one embodiment, the metal-organic polymer composite structure of the present invention is obtained by forming a microphase-separated structure as described below from randomly mixed condition composed of a metal-organic polymer complex and a matrix polymer which is compatible with the complex, thereby introducing ultrafine metal particles into one polymer phase.

[0064] As the matrix polymer into which ultrafine metal particles are to be introduced, there is used a block copolymer which is compatible with the above described "metal-organic polymer complex" in which an ultrafine metal particle is coated with a copolymer, namely, a block copolymer in which a polymer chain which is compatible with "the head portion of the metal-organic polymer complex" and a polymer chain compatible with "the tail portion of the metal-organic polymer complex" are bonded together at each end. Therefore, these polymer chains in the block copolymer for matrix are incompatible with each other. Such a block copolymer for matrix can be used, even if a metal-organic polymer complex in which an ultrafine metal particle is coated with a homopolymer (non-water-soluble organic polymer) is used as "the metal-organic polymer complex", since a polymer chain which is compatible with the homopolymer (a polymer chain which is compatible with the head portion) is contained. The number of blocks of this block copolymer is not particularly limited, and an A-B type diblock copolymer or an A-B-A type triblock copolymer which tends to form a bicontinuous structure is preferred. Requirements for this matrix block copolymer are as follows.

(i) Polymer chain which is compatible with "the head portion of the metal-organic polymer complex"

[0065] This polymer chain is not limited providing it has compatibility with the polymer protecting the metal. For finally producing a metal-organic polymer composite structure, a polymer which further suffices the condition that the supporting structure is not decomposed at room temperature is desired. It is preferred for the structural stabilization of the final porous structure that the glass transition temperature of such polymer chain is higher than room temperature (for example, poly(2-vinylpyridine) and poly(methyl methacrylate) and the like) and/or the monomer unit of the supporting polymer has a crosslinkable functional group (for example, an amino group, imino group, carboxyl group, hydroxyl group, halogen, dimethyl-propoxysilyl group and the like) so that the structure can be fixed by using the corresponding crosslinking agent (for example, poly(2-vinylpyridine) poly(dimethyl-2-propoxysilylstyrene) and the like). The number average molecular weight (Mn) of this polymer chain is not particularly limited, and may be from 1000 to 1000000. From the viewpoint of the easiness for synthesis of the polymer and the easiness for introduction of the ultrafine metal particles into the polymer, Mn of from 5000 to 500000 is preferable.

(ii) Polymer chain compatible with "the tail portion of the metal-polymer complex"

[0066] The number average molecular weight (Mn) of a polymer chain for forming the phase containing the ultrafine metal particle and a polymer chain for protecting the metal is not particularly limited, and may be from 1000 to 1000000. From the viewpoint of the easiness for synthesis of the polymer and easiness for introduction of ultrafine metal particles, Mn of from 5000 to 500000 is preferable.

(3) Formation of microphase-separated structure :

(i) Formation of microphase-separated structure by phase separation of matrix block copolymer

[0067] A "metal-organic polymer complex" (most preferably, a metal-organic polymer complex in which an ultrafine metal particle is coated with a block copolymer) is mixed with the above-described matrix block copolymer, and the mixture is heated to a temperature higher than the "order-disorder transition temperature (T_{ODT})" of the system or the mixture is dissolved in a common solvent for these components, to form "randomly mixed condition (disordered state)" in which all the components are all dissolved. A temperature decrease from this "disordered state" down to the T_{ODT} or lower or a solvent evaporation for concentration (casting) results in a phase separation of the respective polymer chains of the matrix block copolymer to form a microphase-separated structure (most preferably, a bicontinuous structure). For forming such microphase-separated structure, homopolymers homologous to the respective polymers constituting the block copolymer may be mixed in the system. Further, a plasticizer may optionally be added to control the flexibility of the finally formed porous metal-organic polymer composite structure.

[0068] A microphase-separated structure suitable for use as a catalyst, a membrane reactor and other applications is a bicontinuous structure. For obtaining this structure, either the volume ratio of the polymer phase compatible with the metal-organic polymer complex "head portion" or the volume ratio of the polymer phase compatible with the metal-organic polymer complex "tail portion" should be about 0.33, so that a porous structure is formed from the thus obtained metal-organic polymer composite structure. For finally producing a porous metal-organic polymer composite structure from the bicontinuous metal-organic polymer composite structure, the requirements for forming a fine porous material as given in (4) below have to be sufficed.

[0069] During the step of forming the microphase-separated structure, as "the metal-organic polymer complex" (in which an ultrafine metal particle is protectively coated with a block copolymer) is composed of "the head portion" and "the tail portion" as described above, the respective portions will presumably tend to go into the compatible phases of the microphase-separated structure. However, since "the head portion" and "the tail portion" are chemically bonded, the complex can not penetrate deeply into the corresponding phases, and consequently a structure in which ultrafine metal particles are located on the interface of the phase-separated structure.

[0070] For introducing ultrafine metal particles protectively coated with a block copolymer composed of "the head portion" and "the tail portion" into the phase-separated structure from a block copolymer for use as matrix, the two block copolymers are used in a ratio which does not disturb the microphase-separated structure of the matrix polymer.

(ii) Formation of microphase-separated structure from metal-organic polymer complex :

[0071] According to another preferred embodiment of the present invention, only by forming a microphase-separated structure from a metal-organic polymer complex itself (in which the surface of an ultrafine metal particle is coated with a block copolymer) as prepared and purified in the above-described step of (i), there is provided a metal-organic polymer composite structure composed of the phase of a metalphilic polymer containing a high amount of metal and the phase of a metalphobic polymer. For obtaining such structure, a solution or a melt is formed in which the metal-organic polymer complex coated with the block copolymer is randomly mixed (i.e. in a disordered state). In the former case, the solvent is cast (evaporated for concentration), while in the latter case the temperature is decreased down to the T_{ODT} (order-disorder transition temperature) or lower. In general, simply by dissolving a metal-organic polymer complex coated with a block copolymer in a solvent and forming a cast film, a microphase-separated structure from the complex can be produced.

[0072] The type of microphase-separated structure to be produced can be controlled by the volume ratio of the "phase composed of ultrafine metal particles and a metalphilic polymer" or by the volume ratio of the "phase composed of a metalphobic polymer". The volume ratio ϕ of either of the two phases can be related with the type of the structure of the metal-containing phase, generally as follows : $\phi < 0.18$ for sphere, $0.18 < \phi < 0.32$ for cylinder ; $0.32 < \phi < 0.68$ for lamella, and ϕ up to 0.33 for producing a bicontinuous structure. The volume ratio of the metal-containing phase can be controlled to a desired value by controlling the molecular weight ratios of the respective block chains of a block copolymer used for coating the metal, or can be controlled by additionally mixing a homopolymer, an oligomer or a small molecule compatible with the phases. When such homopolymer and the like are mixed, a homopolymer or the like which is compatible with the metalphobic phase is preferably added in the preparation step in order not to decrease the metal content in the phase containing the metal. The homopolymer and the like can contribute to the pore formation by being eluted in the pore formation step as will be described below.

[0073] While this embodiment of the present invention is to obtain the composite structure by a microphase-separated structure from a metal-organic polymer complex itself (composed of an ultrafine metal particle coated with a block copolymer) without substantially using a matrix polymer, for stabilizing the phase-separated structure it is preferable to add a block copolymer, as a reinforcing material, which is the same as the block copolymer used for protectively

coating the ultrafine metal particle or is compatible with such block copolymer, in a small amount so that the metal content does not decrease to 1% or lower.

[0074] While various microphase-separated structures can be produced according to the present invention, the most preferable structure as a catalyst or a membrane reactor is a bicontinuous structure, i.e. a microphase-separated structure in which the two phases composed of the "phase of a metalphilic polymer containing ultrafine metal particles" and the "phase of a metalphobic polymer (in the case of a porous material, this phase forms a pore)" respectively form continuous networks.

(4) Pore formation

[0075] Through the above-described steps, a metal-organic polymer composite structure of the present invention is obtained. For forming a porous structure in which ultrafine metal particles are contained in the support (the phase of a metalphilic polymer) from this structure, the polymer phase not containing the ultrafine metal particles of the microphase-separated structure is removed by using a pore formation methods as described below. These pore formation methods may be utilized in combination.

(i) By selectively decomposing the polymer chain constituting the phase not containing the metal to a size of the monomer unit, a porous metal-organic polymer composite structure is obtained in which ultrafine metal particles are finally introduced into the supporting polymer. A typical polymer applicable to this method is a conjugated diene-based polymer (polybutadiene, polyisoprene and the like) which is conventionally known as the polymer to be subjected to ozonolysis. In utilizing photodecomposition, a polymer which is photodecomposable by specific wavelength absorption, such as poly(methylvinyl ketone) and the like, may be used. The number average molecular weight (M_n) of the polymer is preferably approximately the same as that of the supporting polymer for the formation of the bicontinuous structure, and can be designed depending upon the molecular weight of the support.

(ii) A homopolymer, an oligomer or a small molecule which is homologous and compatible with a metalphobic polymer (the polymer not containing ultrafine metal particles) is added to form a microphase-separated structure (particularly, a bicontinuous structure), and then, the homopolymer, oligomer or small molecule is eluted with a solvent, to form a pore.

In this case, it is not necessary that the polymer chain not containing ultrafine metal particles should be decomposable itself (although it can be decomposable), and any polymer may be applied providing it is incompatible with the supporting polymer chain which supports the ultrafine metal particles. However, since the microphase-separated structure (particularly, the bicontinuous structure) is formed where there is contained the homopolymer, oligomer or small molecule to be finally eluted, it is necessary to design that the molecular weight of the block copolymer is equal to a value calculated by subtracting the volume ratio of such additional homopolymer and the like.

(iii) In addition to the above-described methods, a method can also be used in which there is utilized a block copolymer produced by bonding two polymers at each end in a chemical bond which can be cut by an acid or a base, such as an ion bond, ester bond, amide bond and the like. After the formation of a metal-organic polymer composite structure the interpolymer bond is cut and the phase not containing ultrafine metal particles is dissolved for removal (e.g. Japanese Laid-open Patent No. 279,741/1990).

[0076] A metal-organic polymer composite structure of the present invention thus obtained has a small pore size (tens to several hundreds nm) and a large porosity of, for example, even approx. 50%.

[0077] The following examples further illustrate the features of the present invention, but do not limit the scope thereof.

Example 1

[0078] This Example is an example of the preparation of a metal-organic polymer complex (organic polymer-protected metal cluster complex) in which an ultrafine metal particle is protectively coated with a non-water-soluble organic polymer.

Example 1-1 :

[0079] To a solution of poly(2-vinylpyridine)(hereinafter, abbreviated as P2VP) (M_n (number average molecular weight) = 130,000) and palladium acetylacetonate (hereinafter, abbreviated as Pd(acac)₂) in benzene was added n-propyl alcohol as a reducing agent in the following ratio, and the resultant mixture was heated at 85°C for 48 hours to obtain a Pd cluster complex.

$\text{Pd}(\text{acac})_2$ concentration = 6.6×10^{-4} mol/l

P2VP monomer unit concentration = 2.6×10^{-2} mol/l

n-propyl alcohol concentration = 50% by volume

[0080] The resultant metal cluster has an average particle size of $4.6 \text{ nm} \pm 2.0 \text{ nm}$. The solvent was then evaporated to form a cast film composed of a poly(2-vinylpyridine) film containing metal clusters protected with uniformly dispersed poly(2-vinylpyridine).

Example 1-2 :

[0081] In Example 1-1, the solution after the reaction with heating was once evaporated for drying to solid, and re-dissolved in 1,4-dioxane followed by supercentrifugal separation for 2 hours. The metal cluster protected with the polymer was precipitated as a result. The precipitate was dissolved in 1,4-dioxane and subjected to super-centrifugal separation. This sequential purifying operation was repeated for several times to obtain only the metal cluster protected with poly(2-vinylpyridine) contained therein. The protected metal cluster was stable against various dissolution, condensation, and washing operations.

Example 1-3 :

[0082] In the reaction system of Example 1-1, the polymer concentration and the metal concentration were changed to form protected clusters, and the respective particle sizes were evaluated. As shown in Table 1, it is seen that the protected metal clusters having an approximately constant size irrespective of the reaction condition were obtained. In the case of protection with poly(2-vinylpyridine), the protected particle sizes were constant regardless of the difference in polymer molecular weight, as shown in Table 2.

Table 1

	P2VP monomer unit concentration (mol/l)	Reaction time (hr)				
		2	5	9	24	48
Particle size (nm)	2.6×10^{-2}	4.4 ± 2	4.8 ± 2	5.4 ± 2	5.0 ± 2	4.6 ± 2
	6.5×10^{-3}	4.8 ± 2	5.2 ± 2	5.0 ± 2	5.4 ± 2	5.6 ± 2

Table 2

Molecular weight(Mn)	5000	50000	135000
Particle size(nm)	4.6 ± 2	5.2 ± 2	5.0 ± 2

Example 1-4 :

[0083] To a solution of a block copolymer (hereinafter, abbreviated as P2VP-b-PI ; Mn = (20600)-b-(12600)) composed of poly(2-vinylpyridine) and polyisoprene (hereinafter, abbreviated as PI) and palladium acetylacetonate in benzene was added n-propyl alcohol as a reducing agent in the following ratio, and the resultant mixture was heated at 85 °C for 48 hours to obtain an organic polymer-protected Pd cluster complex.

$\text{Pd}(\text{acac})_2$ concentration = 6.6×10^{-4} mol/l

P2VP monomer unit concentration = 2.6×10^{-2} mol/l

n-propyl alcohol concentration 50% by volume

[0084] The resultant metal cluster has an average particle size of $4 \text{ nm} \pm 2 \text{ nm}$.

Example 1-5 :

[0085] The solution after the reaction in Example 1-4 was once evaporated for drying to solid, and re-dissolved in 1,4-dioxane followed by supercentrifugal separation at 50000 rpm for 2 hours, to precipitate a protected metal cluster, and the precipitate was dissolved in 1,4-dioxane and subjected to supercentrifugal separation. This sequential purifying operation was repeated for several times to obtain only metal cluster complex protected with P2VP-b-PI contained therein. The protected metal cluster thus obtained was stable also against various dissolution and condensation operations. The separated and purified protected metal cluster was then dissolved again in a solution of (P2VP-b-PI : Mn = 20600-b-12600) in benzene to prepare cast film. A P2VP-b-PI film was obtained in which the protected metal clusters did not form large coagulations and were dispersed relatively uniformly.

Example 2

[0086] This example is an example of the preparation of a porous metal-organic polymer composite structure by adding a metal-organic polymer complex (in which an ultrafine metal particle is protectively coated with a homopolymer) to a matrix polymer for forming a microphase-separated structure.

[0087] To a solution of a homopolymer of poly(2-vinylpyridine) (P2VP : Mn = 50000) and palladium acetylacetonate ($\text{Pd}(\text{acac})_2$) in benzene was added n-propyl alcohol as a reducing agent in the following ratio, and the resultant mixture was heated at 85°C for 5 hours to obtain ultrafine Pd particles of which surfaces were protected with P2VP having an average particle size of 4.5 nm.

$$\text{Pd}(\text{acac})_2 \text{ concentration} = 6.6 \times 10^{-4} \text{ mol/l}$$

$$2\text{-vinylpyridine monomer unit concentration} = 2.6 \times 10^{-2} \text{ mol/l}$$

n-propyl alcohol concentration = 50% by volume

[0088] The solution after the reaction was once evaporated for drying to solid, and re-dissolved in 1,4-dioxane followed by supercentrifugal separation at 50000 rpm for 2 hours for several times, so as to purify the ultrafine palladium particles protected with P2VP (abbreviated as $(\text{Pd})_n$ -P2VP). The $(\text{Pd})_n$ -P2VP and a diblock copolymer (P2VP-b-PI : Mn = 23,000 to 17,000) composed of poly(2-vinylpyridine) and polyisoprene was dissolved in chloroform which is a common solvent for these compounds in the following ratio, and further, a polyisoprene homopolymer (PI : Mn = 7,000) and a P2VP homopolymer (Mn = 50,000) were added for controlling the composition.

Solution composition :

[0089]

P2VP-b-PI (Mn = 23,000 to 17,000) = 100 mg

$(\text{Pd})_n$ -P2VP = 0.4 mg

PI (Mn = 7,000) = 30 mg

P2VP (Mn = 50,000) = 16 mg

Solvent ; chloroform = 20 ml

[0090] The solution was cast in a Teflon vessel to form a film having a bicontinuous structure composed of two phases (the thickness of each phase : tens nm) of P2VP phase containing the $(\text{Pd})_n$ -P2VP and the P2VP homopolymer and PI phase containing the PI homopolymer produced by the microphase-separation from the diblock copolymer (P2VP-b-PI).

[0091] This film was dried in a vacuum. Then quaternization reaction of the pyridine with 1,4-diiodobutane was con-

ducted for the crosslinking between the pyridyl groups to fix the shape of the P2VP phase containing $(\text{Pd})_n$ -P2VP. The fixed cast film was washed with hexane to elute the PI homopolymer contained in the PI phase to form a pore through the PI phase. Further, this pore was expanded by ozonolysis of the PI chain which composes the block copolymer. As a result, there was obtained a fine porous membrane (the average pore size and the average matrix width were both tens nm) in which the Pd fine particles having a particle size of about 4 nm were fixed. The resultant fine porous structure had a Pd content of only 0.45% by weight.

Example 3

[0092] This example is an example of the preparation of a porous metal-organic polymer composite structure by forming a microphase-separated structure from a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with a block copolymer.

[0093] To a solution of a block copolymer (P2VP-b-PI) (number average molecular weight $M_n = 23,000$ to $17,000$) composed of poly(2-vinylpyridine)(P2VP) and polyisoprene (PI) and palladium acetylacetonate ($\text{Pd}(\text{acac})_2$) in benzene was added n-propyl alcohol as a reducing agent in the following ratio, and the resultant mixture was heated at 85°C for 50 hours to obtain a metal-organic polymer complex ($(\text{Pd})_n$ -(P2VP-b-PI)) composed of an ultrafine Pd particle of which surface was protected with P2VP-b-PI having an average particle size of 5 nm.

$$\text{Pd}(\text{acac})_2 \text{ concentration} = 6.6 \times 10^{-4} \text{ mol/l}$$

$$\text{2-vinylpyridine monomer unit concentration} = 2.6 \times 10^{-2} \text{ mol/l}$$

$$\text{n-propyl alcohol concentration} = 50\% \text{ by volume}$$

[0094] The solution after the reaction was once evaporated for drying to solid, and re-dissolved in 1,4-dioxane followed by to supercentrifugal separation at 50000 rpm for 2 hours for several times, to purify $(\text{Pd})_n$ -(P2VP-b-PI). The $(\text{Pd})_n$ -(P2VP-b-PI) was dissolved in chloroform, and further, a polyisoprene homopolymer (PI : $M_n = 7,000$) and a P2VP-b-PI ($M_n = 23,000$ to $17,000$) were added for controlling the composition in the following ratio.

Solution composition :

[0095]

Solvent ; chloroform = 100 ml

$(\text{Pd})_n$ -(P2VP-b-PI) = 10 mg

P2VP-b-PI ($M_n = 23,000$ to $17,000$) = 17 mg

PI ($M_n = 17,000$) = 2 mg

[0096] This solution was cast in a Teflon vessel to form a film having a bicontinuous structure in which the $(\text{Pd})_n$ -(P2VP-b-PI) and the diblock copolymer were microphase-separated to $(\text{Pd})_n$ -P2VP phase and PI phase (the thickness of each phase : tens nm).

[0097] This film was dried in a vacuum. Then, quaternization reaction of the pyridine with 1,4-diiodobutane was conducted for the crosslinking between the pyridyl groups to fix the shape of the phase composed of the $(\text{Pd})_n$ and the P2VP. The fixed cast film was then washed with hexane to elute the PI homopolymer contained in the PI phase to form a pore through the PI phase. Further, this pore was expanded by ozonolysis of the PI chain which composes the block copolymer. As a result, there was obtained a fine porous membrane (the average pore size and the average matrix width were both tens nm) in which the ultrafine Pd particles having a particle size of about 5 nm were fixed. This fine porous structure had a metal Pd content of 54% by weight. A electron microphotograph of the resultant fine porous structure is shown in Fig. 5.

Example 4

[0098] This example is an example of the preparation of a porous metal-organic polymer composite structure by adding a metal-organic polymer complex (in which an ultrafine metal particle is coated with a block copolymer) to a

matrix polymer for forming a microphase-separated structure.

[0099] To a solution of a diblock copolymer (P2VP-b-PI : 23,000 to 17,000) composed of poly(2-vinylpyridine)(P2VP) and polyisoprene (PI) and palladium acetylacetonate ($\text{Pd}(\text{acac})_2$) in benzene was added n-propyl alcohol as a reducing agent in the following ratio, and the resultant mixture was heated at 85 °C for 50 hours to obtain a metal-organic polymer complex($(\text{Pd})_n$ -(P2VP-b-PI)) composed of an ultrafine Pd particle of which surface was protected with P2VP-b-PI having an average particle size of 5 nm.

$$\text{Pd}(\text{acac})_2 \text{ concentration} = 6.6 \times 10^{-4} \text{ mol/l}$$

$$\text{2-vinylpyridine monomer unit concentration} = 2.6 \times 10^{-2} \text{ mol/l}$$

$$\text{n-propyl alcohol concentration} = 50\% \text{ by volume}$$

[0100] The solution after the reaction was once evaporated for drying to solid, and re-dissolved in 1,4-dioxane followed by supercentrifugal separation at 50000 rpm for 2 hours for several times, to produce $(\text{Pd})_n$ -(P2VP-b-PI). The $(\text{Pd})_n$ -(P2VP-b-PI) and a matrix polymer (P2VP-b-PI : Mn = 23,000 to 17,000) were dissolved in chloroform, a common solvent for these compounds, in the following ratio. Further, a polyisoprene homopolymer (PI : Mn = 7,000) was added for controlling the composition.

Solution composition :

[0101]

P2VP-b-PI (Mn = 23,000 to 17,000) = 87 mg

$(\text{Pd})_n$ -(P2VP-b-PI) = 3 mg

PI (Mn = 7,000) = 13 mg

Solvent ; chloroform = 20 ml

[0102] This solution was cast in a Teflon vessel to form a film having a bicontinuous structure composed of two phases (the thickness of each phase : tens nm) of P2VP phase containing the $(\text{Pd})_n$ -P2VP and PI phase containing the PI homopolymer, produced by the microphase-separation from the matrix polymer (P2VP-b-PI).

[0103] This film was dried in a vacuum. Then, quaternization reaction of the pyridine with 1,4-diiodobutane was conducted for the crosslinking between the pyridyl groups to fix the shape of the P2VP phase containing the ultrafine Pd particles in the interface. The fixed cast film was washed with hexane to elute the PI homopolymer contained in the PI phase to form a pore through the PI phase. Further, this pore was expanded by ozonolysis of the PI chain which composes the block copolymer. As a result, there was obtained a fine porous membrane of P2VP (the average pore size and the average matrix width were both tens nm) in which the ultrafine Pd particles having a particle size of about 5 nm were fixed on the interface (Fig. 4).

Claims

1. A method for producing a porous metal-organic polymer composite structure comprising a microphase-separated structure from a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain which are incompatible with each other are bonded together at each end, wherein ultrafine metal particles are contained in the metalphilic polymer phase of said microphase-separated structure, comprising the steps of:

i) dissolving a non-water-soluble organic polymer, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with the non-water-soluble organic polymer,

ii) producing a solution or a melt in which said metal-organic polymer complex and a matrix block copolymer compatible with the complex are randomly mixed, and forming a microphase-separated structure from said

matrix block copolymer by a solvent casting or a decrease in temperature, thereby introducing the ultrafine metal particles into the metalphilic polymer phase, and

iii) removing the metalphobic polymer phase from said microphase-separated structure for pore formation by eluting or decomposing said metalphobic polymer phase.

2. The method according to claim 1, wherein, as the non-water-soluble organic polymer, a block copolymer is used in which a metalphilic polymer chain and a metalphobic polymer chain which are incompatible with each other are bonded together at each end, so as to obtain a metal-organic polymer composite structure in which ultrafine metal particles are located near the skeleton boundary of the metalphilic polymer phase of the microphase-separated structure.
3. The method according to claim 1, wherein, as the non-water-soluble organic polymer, a homopolymer composed of a metalphilic polymer chain is used, so as to obtain a metal-organic polymer composite structure in which ultrafine metal particles are located deeply inside and around the center of the metalphilic polymer phase of the microphase-separated structure.
4. The method according to claim 2 or claim 3, wherein in the step of forming the microphase-separated structure, a homopolymer which is compatible with the metalphobic polymer is added, and in the step of pore formation, said homopolymer is eluted.
5. A method for producing a porous metal-organic polymer composite structure comprising a microphase-separated structure from a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain which are incompatible with each other are bonded together at each end, wherein ultrafine metal particles are contained in the metalphilic polymer phase of said microphase-separated structure, comprising the steps of:
 - i) dissolving a block copolymer in which a metalphilic polymer chain and a metalphobic polymer chain are bonded together at each end, a solvent-soluble metal compound and a reducing agent in an organic solvent, and then heating the solution for reduction at 50 to 120°C to produce a metal-organic polymer complex in which an ultrafine metal particle is protectively coated with said block copolymer, and
 - ii) producing a solution or a melt in which said metal-organic polymer complex is randomly mixed, and forming a microphase-separated structure from said metal-organic polymer complex by a solvent casting or a decrease in temperature, and
 - iii) removing the metalphobic polymer phase from said microphase-separated structure for pore formation by eluting or decomposing said metalphobic polymer phase.
6. The method according to claim 5, wherein in the step of forming the microphase-separated structure, a homopolymer which is compatible with the metalphobic polymer is added, and in the step of pore formation, said homopolymer is eluted.

Patentansprüche

1. Ein Verfahren zur Herstellung eines porösen, metallorganischen Polymer-Verbundbauteil umfassend eine Mikrophasen-separierte Struktur eines Blockcopolymers, in welchem eine metallophile Polymerkette und eine metallophobe Polymerkette, die zueinander inkompatibel sind, an jedem Ende aneinander gebunden sind, wobei in der metallophilen Polymerphase der besagten Mikrophasen-separierten Struktur ultrafeine Metallpartikel enthalten sind, umfassend die folgenden Schritte:
 - i) Auflösen eines wasserunlöslichen organischen Polymers, einer in einem Lösungsmittel löslichen Metallverbindung und eines Reduktionsmittels in einem organischen Lösungsmittel, anschließende Erwärmung der Lösung zur Reduktion bei 50 bis 120° C, um einen metallorganischen Polymerkomplex herzustellen, indem ein ultrafeines Metallpartikel mit dem wasserunlöslichen organischen Polymer geschützt umhüllt ist,
 - ii) Herstellung einer Lösung oder einer Schmelze, in der der besagte metallorganische Polymerkomplex und ein Matrix-Blockcopolymer, das mit dem Komplex kompatibel ist, wahllos gemischt wird, und Bildung einer

Mikrophasen-separierten Struktur aus dem besagten Matrix-Blockcopolymer durch Abgießen des Lösungsmittels oder eine Temperatursenkung, wobei die ultrafeinen Metallpartikel in die metallophile Polymerphase eingebracht werden, und

- 5 iii) Entfernung der metallophoben Polymerphase von der besagten Mikrophasen-separierten Struktur zur Porenbildung durch Herauslösen oder Zersetzung der besagten metallophoben Polymerphase.
2. Verfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** als wasserunlösliches organisches Polymer ein Blockcopolymer verwendet wird, in dem eine metallophile Polymerkette und eine metallophobe Polymerkette, die
10 zueinander inkompatibel sind, an jedem Ende aneinander gebunden sind, um ein metallorganisches Polymer-Verbundbauteil zu erhalten, in dem ultrafeine Metallpartikel in der Nähe des Endes des Gerüsts der metallischen Polymerphase der Mikrophasen-separierten Struktur angeordnet sind.
3. Verfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** als wasserunlösliches organisches Polymer ein Homopolymer, zusammengesetzt aus einer metallophilen Polymerkette, verwendet wird, um ein metallorganisches Polymer-Verbundbauteil zu erhalten, in dem ultrafeine Metallpartikel tief im Inneren und in der Nähe des
15 Zentrums der metallophilen Polymerphase der Mikrophasen-separierten Struktur angeordnet sind.
4. Verfahren nach Anspruch 2 oder Anspruch 3, **dadurch gekennzeichnet, dass** beim Schritt der Bildung der Mikrophasen-separierten Struktur ein Homopolymer, das mit dem metallophoben Polymer kompatibel ist, zugesetzt
20 wird und beim Schritt der Porenbildung das besagte Homopolymer ausgewaschen wird.
5. Verfahren zur Herstellung eines porösen metallorganischen Polymer-Verbundbauteils enthaltend eine Mikrophasen-separierte Struktur eines Blockcopolymers, in welchem eine metallophile Polymerkette und eine metallophobe Polymerkette, die zueinander inkompatibel sind, an jedem Ende aneinander gebunden sind, wobei in der metallophilen Polymerphase der besagten Mikrophasen-separierten Struktur ultrafeine Metallpartikel enthalten sind, umfassend die folgenden Schritte:
25
- i) Auflösen eines Blockcopolymers, in dem eine metallophile Polymerkette und eine metallophobe Polymerkette an jedem Ende aneinander gebunden sind, einer in einem Lösungsmittel löslichen Metallverbindung und eines Reduktionsmittels in einem organischen Lösungsmittel, anschließend Erwärmen der Lösung auf 50 bis 120° C zur Reduktion, um einen metallorganischen Polymerkomplex herzustellen, in dem ein ultrafeines Metallpartikel durch das besagte Blockcopolymer geschützt umhüllt ist, und
30
- ii) Herstellung einer Lösung oder einer Schmelze, indem der besagte metallorganische Polymerkomplex wahllos gemischt ist, und eine Mikrophasen-separierte Struktur aus dem besagten metallorganischen Polymerkomplex durch Lösungsmittel auswaschen oder eine Verminderung der Temperatur gebildet wird und
35
- iii) Entfernung der metallophoben Polymerphase von der besagten Mikrophasen-separierten Struktur zur Porenbildung durch Auswaschen oder Zersetzen der besagten metallophoben Polymerphase.
40
6. Verfahren nach Anspruch 5, **dadurch gekennzeichnet, dass** beim Schritt der Bildung der Mikrophasen-separierten Struktur, ein Homopolymer, das mit dem metallophoben Polymer kompatibel ist, zugesetzt wird, und beim Schritt der Porenbildung das besagte Homopolymer ausgewaschen wird.
45

Revendications

1. Procédé de production d'une structure composite polymère organique - métal poreux comprenant une structure séparée en microphases à partir d'un copolymère séquencé dans lequel une chaîne polymère metallophile et une chaîne polymère metallophobe qui sont incompatibles l'une avec l'autre sont liées l'une à l'autre à chaque extrémité, dans lequel des particules de métal ultrafines sont contenues dans la phase polymère metallophile de ladite structure séparée en microphases, comprenant les étapes consistant à :
50
- i) dissoudre un polymère organique non-hydrosoluble, un composé métallique soluble dans un solvant et un agent de réduction dans un solvant organique, puis à chauffer la solution pour la réduction à 50 à 120°C pour produire un complexe polymère organique - métal dans lequel une particule de métal ultrafine est enduite pour protection du polymère organique non-hydrosoluble,
55

ii) produire une solution ou une fusion dans laquelle ledit complexe polymère organique - métal et un copolymère séquencé et matriciel compatible avec le complexe sont mélangés de manière aléatoire, et former une structure séparée en microphases à partir dudit copolymère séquencé et matriciel par une coulée de solvant ou une diminution de la température, introduisant ainsi les particules de métal ultrafines dans la phase polymère métallophile, et

iii) retirer la phase polymère métallophile de ladite structure séparée en microphases pour la formation de pores en éluant ou en décomposant ladite phase polymère métallophile.

2. Procédé selon la revendication 1, dans lequel, en tant que le polymère organique non-hydrosoluble, un copolymère séquencé est utilisé dans lequel une chaîne polymère métallophile et une chaîne polymère métallophobe qui sont incompatibles l'une avec l'autre sont liées l'une à l'autre à chaque extrémité, de manière à obtenir une structure composite polymère organique - métal dans laquelle des particules de métal ultrafines sont situées près de la limite du squelette de la phase polymère métallophile de la structure séparée en microphases.

3. Procédé selon la revendication 1, dans lequel, en tant que le polymère organique non-hydrosoluble, un homopolymère composé d'une chaîne polymère métallophile est utilisé, de manière à obtenir une structure composite polymère organique - métal dans laquelle les particules de métal ultrafines sont situées profondément à l'intérieur et autour du centre de la phase polymère métallophile de la structure séparée en microphases.

4. Procédé selon la revendication 2 ou la revendication 3, dans lequel dans l'étape consistant à former la structure séparée en microphases, un homopolymère qui est compatible avec le polymère métallophobe est ajouté, et dans l'étape de la formation de pores, ledit homopolymère est élué.

5. Procédé de production d'une structure composite polymère organique - métal poreux comprenant une structure séparée en microphases d'un copolymère séquencé dans lequel une chaîne polymère métallophile et une chaîne polymère métallophobe qui sont incompatibles l'une avec l'autre sont liées l'une à l'autre à chaque extrémité, dans lequel des particules de métal ultrafines sont contenues dans la phase polymère métallophile de ladite structure séparée en microphases, comprenant les étapes consistant à :

i) dissoudre un copolymère séquencé dans lequel une chaîne polymère métallophile et une chaîne polymère métallophobe sont liées l'une à l'autre à chaque extrémité, un composé métallique soluble dans un solvant et un agent de réduction dans un solvant organique, puis chauffer la solution pour la réduction à 50 à 120°C pour produire un complexe polymère organique - métal dans lequel une particule de métal ultrafine est enduite pour protection dudit copolymère séquencé, et

ii) produire une solution ou une fusion dans laquelle un complexe polymère organique - métal est mélangé de manière aléatoire, et former une structure séparée en microphases à partir dudit complexe polymère organique - métal par une coulée de solvant ou une diminution de température, et

iii) retirer la phase polymère métallophobe de ladite structure séparée en microphases pour la formation de pores en éluant ou en décomposant ladite phase polymère métallophobe.

6. Procédé selon la revendication 5, dans lequel dans l'étape consistant à former la structure séparée en microphases, un homopolymère qui est compatible avec le polymère métallophobe est ajouté, et dans l'étape de formation de pores, ledit homopolymère est élué.

Figure 1





Figure 2






Figure 3






Figure 4

Figure 5



(A)



(B)